



beyond our customer's expectations since 1974

111111111

MAYFAIR is a contemporary series that displays subtle movement and colour variation for a soft limestone look. Available in four colours and two finishes, MAYFAIR is able to add extra design elements to any environment.



PRODUCT TYPE: Glazed porcelain

COLOURS: Cream, Putty, Taupe and Dark Taupe

SIZES: 300x300mm, 300x600mm and 600x600mm

Rectified Edges

FINISHES/USAGE: Matt and Grip/Wall and Floor

AESTHETIC QUALITIES: Subtle movement and colour variation

ORIGIN: N/A

TECHNICAL DATA: P3 Pendulum slip rating/Matt

P5 Pendulum slip rating/Grip

More technical data on last page

VARIATION:



125-135 Bonds Rd Riverwood NSW 2210, AUSTRALIA | T +61 2 9584 4000 | W www.aceceramics.com.au | E sales@aceceramics.com.au

Dark Taupe



beyond our customer's expectations since 1974

PRODUCT INFORMATION



Cream

Matt 300x300mm | 300x600mm | 600x600mm



Taupe


Matt 300x300mm | 300x600mm | 600x600mm



Matt 300x300mm | 300x600mm | 600x600mm Grip 300x600mm



Matt 300x300mm | 300x600mm | 600x600mm Grip 300x600mm



Variation is an inherent property of tiles and stone. Sizes are nominal and may include a joint.

125-135 Bonds Rd Riverwood NSW 2210, AUSTRALIA | T +61 2 9584 4000 | W www.aceceramics.com.au | E sales@aceceramics.com.au



MAYFAIR DARK TAUPE




Variation is an inherent property of tiles and stone. Sizes are nominal and may include a joint.



125-135 Bonds Rd Riverwood NSW 2210, AUSTRALIA | T +61 2 9584 4000 | W www.aceceramics.com.au | E sales@aceceramics.com.au


CREAM VARIATION





125-135 Bonds Rd Riverwood NSW 2210, AUSTRALIA | T +61 2 9584 4000 | W www.aceceramics.com.au | E sales@aceceramics.com.au


PUTTY VARIATION





125-135 Bonds Rd Riverwood NSW 2210, AUSTRALIA | T +61 2 9584 4000 | W www.aceceramics.com.au | E sales@aceceramics.com.au

TAUPE VARIATION




aceceramics

125-135 Bonds Rd Riverwood NSW 2210, AUSTRALIA | T +61 2 9584 4000 | W www.aceceramics.com.au | E sales@aceceramics.com.au

beyond our customer's expectations since 1974

DARK TAUPE VARIATION





125-135 Bonds Rd Riverwood NSW 2210, AUSTRALIA | T +61 2 9584 4000 | W www.aceceramics.com.au | E sales@aceceramics.com.au

TECHNICAL DATA

Technic	eal Characteristi s	Test Method	Requirement	Result
Surface	quality	ISO 10545-2	95%	100%
Length	and Width	ISO 10545-2	‡ 0,6%	0.5%
Thickne	ess	ISO 10545-2	‡ 0,5	‡ 0,5
Straight	ness of sides	ISO 10545-2	‡ 0,5%	‡ 0,3%
Water A	bsorbtion	ISO 10545-3	3%	3%
Modulu	s of Rupture	ISO 10545-4	35	38
Breakin	g Strength	ISO 10545-4	1100	1300
Crazing	Resistance	ISO 10545-11	Pass	Resistant
Chemic	al Resistance	ISO 10545-13	Declared Value	ULA / UHB
Stain Re	esistance	ISO 10545-14	Minimum Class 3	Class 5